



PRODUCT HIGHLIGHTS: (PRODUCT CODE - 1104HBG)

- Product comparable to IPS 711/717 and Oatey PVC HD Gray.
- Premium, UPVC/PVC Solvent cement for residential and commercial water systems.
- High performance fast set cement that delivers a strong permanent bond. Formatted for use without a primer if local codes permit.
- Heavy bodied UPVC/PVC cement designed for copper tube size (UPVC/PVC) potable water pipe and fittings up to 12" (315 mm).

GENERAL DESCRIPTION:

Suretite HD Gray PVC Solvent cement by Arrow Adhesive is a clear, low VOC emission, medium bodied, fast setting, high strength cement for PVC pipe and fittings with interference fit through 12 inch (315 mm) diameter.

PHYSICAL/CHEMICAL PROPERTIES:

Appearance Gray Syrupy Liquid
Resin PVC
Viscosity min. 1600 cps @ 73° F +- 2° F
Maximum VOC per SCAQMD 1168/316A or BAAQMD
Method 40: 510 g/L

STANDARD TECHNICAL INFORMATION ON SOLVENT CEMENT:

Note: The above mentioned performance of solvent cements are under lab conditions. There may be variance under field conditions based on weather, temperature, individual handling & pipe characteristics.

Average initial SET - under lab condition. Field conditions & timings may vary

initial set is the necessary time to allow before the joint can be carefully handled
Allow 50% extra time during damp or humid weather.

Temperature	1/2" - 1 1/4"	1 1/2" - 2"	2 1/2" - 8"	10" - 15"	15" +
Below 5°C	10 minutes	15 minutes	12 hrs	24 hrs	48 hrs
5-16°C	5 minutes	10 minutes	2 hrs	8 hrs	16 hrs
16°C & Above	2 minutes	5 minutes	30 minutes	2 hrs	4 hrs

Joint cure schedule for testing at 15Kg pressure. 7 Kg for 10" and above

Joint cure time is necessary time to allow before the joint can be pressurized
Allow 50% extra time during damp or humid weather.

Allow 2-3 times extra time for industrial applications

Temperature	1/2" - 1 1/4"	1 1/2" - 2"	2 1/2" - 8"	10" - 15"	15" +
Below 5°C	48 hrs	96 hrs	8 days	8 days	14 days
5-16°C	12 hrs	24 hrs	48 hrs	96 hrs	6 days
16°C & Above	6 hrs	12 hrs	24 hrs	48 hrs	72 hrs

Average no of joints per liter of solvent cement this is as per lab tests Field conditions may vary

Pipe dia inch	No of joints
1/2"	300
3/4"	200
1"	125
1 1/2"	90
2"	60
3"	40
4"	30
6"	10
8"	5
10"	2-3
12"	1-2

AVAILABILITY:

PRODUCT NUMBER	SIZE	(Inner carton) PACK	(Master carton) PACK	CARTON WEIGHT (KG)
1104HBG16	16 oz./473 ml	24	24	15.20
1104HBG32	32 oz./ 946 ml	12	12	12.50

APPLICATION:

Read all directions carefully before using this product. Do not breathe vapors. Use only in well ventilated areas. If forced air ventilation is used, be sure it does not cause a fire hazard from solvent vapors. If adequate ventilation cannot be provided, wear a NIOSH-approved respirator for organic solvents. Do not use or store near heat, sparks, or flames. Do not smoke, eat or drink when using. Do not take internally. Vapors may accumulate in low places and may ignite explosively. Store and use at temperature between 0°F to 110°F. At temperatures outside of this range, special care must be taken to prepare good joints and prevent exposures to solvents. Stir or shake before using; if jelly-like, don't use. Keep container closed when not in use. Avoid eye and skin contact - wear safety glasses with side shields and wear rubber gloves.

1. Square pipe ends and remove all burrs and dirt.
2. Check dry fit of pipe and fitting. Pipe should easily go 1/3 of the way into the fitting. If the pipe bottoms, it should be snug.
3. Use a suitable applicator at least 1/2 the size of the pipe diameter. For larger size pipe systems use a natural bristle brush or roller.
4. Clean pipe and fitting with a listed primer.
5. Apply liberal coat of cement to pipe to the depth of the socket; leave no uncoated surface.
6. Apply a thin coat of cement to inside of fitting; avoid puddling of cement. Puddling can cause weakening and premature failure of pipe or fitting. apply a second coat of cement to the pipe.
7. Assemble parts QUICKLY. Cement must be fluid. If cement surface has dried, recoat both parts.
8. Push pipe FULLY into fitting using a 1/4 turning motion until pipe bottoms.
9. Hold pipe and fitting together for 30 seconds to prevent pipe push -out-longer at low temperatures. Wipe off excess.
10. Allow 15 minutes for good handling strength. For temperature above 60°F allow for 2 hour cure time before pressure testing up to 180 psi. Longer cure times may be required depending on pipe diameter, pressure and weather. DO NOT TEST WITH AIR.

This product is not for caustic or acidic chemical solutions. Consult Arrow Adhesive Technical department for more information.

STANDARDS:

- Meets ASTM D 2564 Standards.
- Meets SCAQMD Rule 1168/316A.
- Compliant with LEED (Leadership in Energy and Environment Design).
- Compliant with ASTM F 493, ANSI Standard 14 and ANSI Standard 61 for use in potable drain, waste, vent and sewer applications.

SHELF LIFE:

2 years in tightly sealed containers from the date code of manufacture as stamped on the bottom of the container. Stability of the product is limited by the evaporation of the solvent when the container is opened. Evaporation of solvent will cause the cement to thicken and reduce its effectiveness. To be stored in cool, dry environment below 35°C.

QUALITY ASSURANCE:

Suretite HD GRAY PVC solvent cement by Arrow Adhesive is carefully evaluated to assure that consistent high quality is maintained. A batch identification code is stamped on each can and assures traceability of all materials and processes used in manufacturing this solvent cement.

PRECAUTIONS:

Fire Use dry chemical, foam, or carbon dioxide extinguisher. Water spray may be applied to reduce potential vapors or for cooling. Burning liquid extinguished with water will float and may re-ignite on surface of water.

Spill Remove all sources of ignition and ventilate area. Personnel cleaning up spill should wear appropriate personal protective equipment, including respirators if vapor concentrations are high. Soak up spill with absorbent material. Put absorbent material in covered, labeled metal containers. Dispose of in accordance with local regulations.
DO NOT REUSE EMPTY CONTAINER. KEEP OUT OF REACH OF CHILDREN.

FIRST AID:

Ingestion: If swallowed, **Do not induce vomiting.** Drink Water and call a doctor or poison control immediately.

FIRST AID INSTRUCTIONS CALL +91 97697 19453

Inhalation: If overcome with vapors, remove to fresh air. If not breathing, give artificial respiration.

If breathing is difficult, give oxygen. Call a physician.

Eye Contact: Flush with plenty of water for 15 minutes and call a physician.

Skin Contact: Wash skin with plenty of water and soap for at least 15 minutes.
If irritation develops, get medical attention.

SPECIAL PRECAUTION:

Do not use a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with PVC and CPVC solvent cement and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify line by pumping water into the piping system- this solution will be nonvolatile. Further more, dry granules calcium hypochlorite should not be stored or used near solvent cements and primers.

IMPORTANT NOTE:

This product is intended for use by skilled individual at their own risk. These suggestions and data are based on information we believe to be reliable. Installer should verify for themselves that they can make satisfactory joints under varying conditions. Towards this end, It is highly desirable that they receive personal instruction from trained instructors or experienced installers. Contact Arrow Adhesive or your supplier for additional information or instructions.

WARRANTY:

Arrow Adhesive warrants that all new Arrow Adhesive products shall be good quality and free from defects in material and workmanship for shelf life as indicated on the product. If any Arrow Adhesive product becomes defective, or fails to conform to our written limited warranty under normal use and storage conditions, Then Arrow Adhesive will without charge, replace the non conforming product. However, this limited warranty shall not extend to, nor shall Arrow Adhesive be responsible for, damage or loss resulting from accident, misuse, negligent use, improper application, or incorporation of Arrow Adhesive product into other products. In addition any repackaging of Arrow Adhesive products also shall void the limited warranty. Arrow Adhesive shall not be responsible for, nor does this limited warranty extend to, consequential damage or incidental damage or expense, including without limitation, injury to persons or property or loss of use. Please refer to our standard Arrow Adhesive warranty for additional provisions.

**IPS is a trademark of IPS Corp, USA*

**Oatey is a trademark of Oatey USA*